

<b>HD689D(531-BPD)</b>							
<b>DATE OF TESTED</b>		2019/6/30					
<b>APPLICABLE STANDARD</b>		QB/T 2476-2000					
<b>FINISH DESCRIPTION</b>		仿金	POLISHED COPPER				
<b>mateiral grade</b>		chemical composition					
<b>REFERENCE</b>		<b>TENSILE STRENGTH Mpa</b>	<b>PB</b>	<b>N1</b>	<b>Cr</b>	<b>Cu</b>	<b>FE</b>
<b>BRASS</b>		480	2.0~2.8	1	0	59	0.5
<b>DESCRIPTIONS OF GOODS</b>	<b>TEST ITEMS</b>	范围	STANDARD	<b>TEST DATA</b>		CONCLUSION	
				NO.1	NO.2		
Cylindrical lock	<b>SURFACE ROUGHNESS</b>	表面粗糙度	Ra≤6.3 μm	6.2	6.1	PASS	
	<b>LATCH LATERAL STATIC LOAD</b>	锁舌侧向静负荷	1500N	1500N	1500N	PASS	
	<b>Handle the axial tensile force</b>	执手轴向静拉力	1000N	1000N	1000N	PASS	
	<b>Handle the radial static load</b>	执手径向静载荷	800N	800N	800N	PASS	
	<b>Key unlocking torque</b>	钥匙开锁力矩	N.M≤1	1	1	PASS	
	<b>Pull out key</b>	钥匙拔出静拉力	N≤8	6	6.5	PASS	
<b>PICTURE</b>							