

HD662D(588BK-AC)									
DATE OF TESTED		2019/6/30							
APPLICABLE STANDARD		QB/T 2476-2000							
FINISH DESCRIPTION		红古	ANTIQUE COPPER						
mateiral grade			chemical composition						
REFERENCE		TENSILE STRENGTH Mpa	C	SI	Cr	NI	S	P	Mn
STEEL		480	0.12	1	18	0.06	0.03	0.04	1
DESCRIPTIONS OF GOODS	TEST ITEMS	范围	STANDARD	TEST DATA		CONCLUSION			
				NO.1	NO.2				
Cylindrical lock	SURFACE ROUGHNESS	表面粗糙度	Ra≤6.3 μm	6.2	6.1	PASS			
	LATCH LATERAL STATIC LOAD	锁舌侧向静负荷	1500N	1500N	1500N	PASS			
	Handle the axial tensile force	执手轴向静拉力	1000N	1000N	1000N	PASS			
	Handle the radial static load	执手径向静载荷	800N	800N	800N	PASS			
	Key unlocking torque	钥匙开锁力矩	N.M≤1	1	1	PASS			
	Pull out key	钥匙拔出静拉力	N≤8	6	6.5	PASS			
PICTURE									
									